

# **Comtech Grout EP40**

Two component colored epoxy chemical resistant tile grout.

### **Description:**

*Comtech Grout EP40* is a two component solvent free epoxy resin based tile grout.

The components are mixed together to give a smooth non-slump colored grout that suits all types of tiles.

**Comtech Grout EP40** consists of a blend of specially selected resins, curing agents, graded inert acid resistant fillers and a

unique colour pack system.

## Uses & Advantages:

- Easy to apply
- Attractive appearance with wide range of colors as per colors table.
- Easy to clean up during application can be washed off with water.
- Long working life
- Waterproof
- High resistance to a wide range of industrial chemicals
- Good adhesion to types of tile
- Good to use in wet area, fountains, swimming pool, kitchen, bathroom and Sauna

# **Typical properties:**

Color	As per the table
Density	1750 Kg/m <sup>3</sup>
Compressive	40 MPa @ 1 day
Strength	85 MPa @ 7 days
(BS 1881, Pt 116)	
@ 25°C	
Flexural strength	33 MPa @ 7 days
(ASTM C 580 part 7)	
@ 25°C	
Tensile Strength	16 Mpa @ 7 days
(BS 6319)	
Pot Life	40 minutes
@ 30 °C	
Initial cure	12 Hours
@ 30 °C	
Service temperature	0 to 85 °C

 Middle East Bldg. Chemical Ind. LLC
 الشرق الأوسط لصناعة كيماويات البناء ذ م م

 P.O.Box 47611, Sharjah, UAE, Tel. (9716) 544 18 73, Fax (9716) 544 18 79. Industrial License 557094

 www.comtech-uae.com

 info@comtech-uae.com

 Comtech Construction Products Inc
 2870 Gessner Rd. Houston - TX 77080 +1(713) 517 4081



# Packing & Yield:

A 7kg set of **Comtech Grout EP40** will cover an average of 14 to 20m<sup>2</sup> depend on tile size.

# Chemical resistant:

**Comtech Grout EP40** has an excellent resistance to a wide range of chemicals commonly encountered in industrial applications like: Nitric acid 25%

Hydrochloric acid 50% Phosphoric acid 50% Acetic acid 10% Sulphuric acid 50% Lactic acid 10% Citric acid Petrol, Oil, Kerosene Butanol Sodium Hydroxide 50% Ammonia (880) 10%

#### Application:

Apply **Comtech Grout EP40 to** the spaces between tiles during working time the mixture using scraper or spatula directly into the joints and around the edges.

Remove surplus material from the face of the tiles with a dry cloth, it may be necessary to use small quantities of solvent to assist in the cleaning process.

## Health and safety:

**Comtech Grout EP40** does not classified in the hazardous materials; however it should not be allowed to come into prolonged contact with skin and eyes.

The normal safety precautions (hand gloves & safety goggles) are recommended for handling.

The first aid if some harm happened with eyes is to wash with water.

# Method of use:

#### Surface preparation:

Remove all grease, oil, dust, residual or other contaminant that could impair adhesion. Laitance should preferably be removed.

#### Mixing:

Thoroughly stir Part A, add Part B and blend thoroughly using a slow speed mixer fitted with a suitable paddle till homogenous color is achieved. WARRANTY STATEMENT: The information given here is based on our knowledge, and we believe it to be true and accurate.

We assume no responsibility for the use of these information, recommendations or suggestions.

Users should always refer to the most recent issue of the technical data sheet for the product concerned copies of which will be supplied on request.



 Middle East Bldg. Chemical Ind. LLC
 الشرق الأوسط لصناعة كيماويات البناء ذ م م

 P.O.Box 47611, Shariah, UAE, Tel. (9716) 544 18 73, Fax (9716) 544 18 79, Industrial License 557094


 www.comtech-uae.com

 info@comtech-uae.com

 Comtech Construction Products Inc
 2870 Gessner Rd. Houston - TX 77080 +1(713) 517 4081



## STANDARD COLORS



Middle East Bldg. Chemical Ind. LLC الشرق الأوسط لصناعة كيماويات البناء ذ م م P.O.Box 47611, Sharjah, UAE, Tel. (9716) 544 18 73, Fax (9716) 544 18 79, Industrial License 557094 www.comtech-uae.com info@comtech-uae.com Comtech Construction Products Inc 2870 Gessner Rd. Houston - TX 77080 +1(713) 517 4081